

**Flat gasket for weld neck flange DIN 2633**

Suitable for hydrocarbons such as oils or solvents, alcohols, glycols, aqueous solutions, water and steam up to 200 °C, as well as weak alkalis and organic acids.

The material is conditionally suitable for ketones and esters, chlorinated solvents, as well as strong alkalis and inorganic acids.

material Centellen WS 3820, aramid fibers, bound with NBR

| DN | | order-no. |
|-----|------------------|-------------|
| 50 | 107 x 61 x 2 mm | 2305 050000 |
| 65 | 127 x 77 x 2 mm | 2305 065000 |
| 80 | 142 x 90 x 2 mm | 2305 080000 |
| 100 | 162 x 115 x 2 mm | 2305 100000 |
| 125 | 192 x 141 x 2 mm | 2305 125000 |
| 150 | 218 x 169 x 2 mm | 2305 150000 |
| 200 | 273 x 220 x 2 mm | 2305 200000 |